

1 ***(December 2, 2002)***

2 ***Epoxy Mortar***

3 Epoxy mortar shall be composed of one part of epoxy bonding agent, Type III,
4 as specified in Section 9-26.1, and two parts of clean, fine grained sand, by
5 volume. The grade and class of epoxy bonding agent shall be as recommended
6 by the resin manufacturer and approved by the Engineer.